

CERTIFICATE OF MAILING BY FIRST CLASS MAIL (37 CFR 1.8)

Applicant(s): Kiyohisa TAKAHASHI et al.

Docket No.

2003JP306

Serial No.

10/565,113

Filing Date

January 17, 2006

Examiner

ASHTON, Rosemary E.

Group Art Unit


1752

Invention: **MATERIAL FOR FORMING PATTERN AND METHOD FOR FORMING FINE PATTERN
USING THE SAME**

I hereby certify that this EP 1 757 989 A1 - 16 Pages*(Identify type of correspondence)*

is being deposited with the United States Postal Service as first class mail in an envelope addressed to: The

Commissioner of Patents and Trademarks, Washington, D.C. 20231-0001 on

April 4, 2007*(Date)*MARIA T. SANCHEZ*(Typed or Printed Name of Person Mailing Correspondence)*
*(Signature of Person Mailing Correspondence)***Note: Each paper must have its own certificate of mailing.**



(11) **EP 1 757 989 A1**

(12) **EUROPEAN PATENT APPLICATION**
published in accordance with Art. 158(3) EPC

(43) Date of publication:
28.02.2007 Bulletin 2007/09

(51) Int Cl.:
G03F 7/40 (2006.01) H01L 21/027 (2006.01)

(21) Application number: **05728791.4**

(86) International application number:
PCT/JP2005/006961

(22) Date of filing: **08.04.2005**

(87) International publication number:
WO 2005/098545 (20.10.2005 Gazette 2005/42)

(84) Designated Contracting States:
BE DE FR IT

(30) Priority: **09.04.2004 JP 2004115872**

(71) Applicant: **AZ Electronic Materials USA Corp.**
Somerville, NJ 08876 (US)

(72) Inventors:
• **NISHIBE, Takeshi,**
c/o AZ Electronic Materials KK
Shizuoka 43714 12 (JP)
• **HONG, Sung Eun,**
c/o AZ Electronic Materials KK
Shizuoka 43714 12 (JP)


• **TAKANO, Yusuke,**
c/o AZ Electronic Materials KK
Shizuoka 43714 12 (JP)
• **OKAYASO, Tetsue,**
c/o AZ Electronic Materials KK
Shizuoka 43714 12 (JP)

(74) Representative: **Isenbruck, Günter**
Isenbruck Bösl Hörschler
Wichmann Huhn
Patentanwälte
Theodor-Heuss-Anlage 12
D-68165 Mannheim (DE)

(54) **WATER-SOLUBLE RESIN COMPOSITION AND METHOD OF FORMING PATTERN THEREWITH**

(57) In the present invention, in a water soluble resin composition for use in a method for pattern formation in which a covering layer is provided on a resist pattern formed of a radiation-sensitive resin composition capable of coping with ArF exposure to increase the width of the resist pattern and thus to realize effective formation of higher density trench or hole pattern, the size reduction level of the resist pattern layer can be further increased as compared with that in the prior art technique, and, in addition, the size reduction level dependency of the coarse-and-fine resist pattern can be reduced. A method for pattern formation using the water soluble resin composition is also provided. The water soluble resin composition which is usable for the method for pattern formation applicable to ArF excimer laser irradiation comprises a water soluble resin, an acid generating agent capable of generating an acid upon heating, a surfactant, a crosslinking agent, and a water-containing solvent.

Fig. 1



EP 1 757 989 A1

Description**BACKGROUND OF THE INVENTION****5 Field of the Invention**

[0001] The present invention relates to a method for resist pattern formation in which, in the formation of a resist pattern in a semiconductor or the like manufacturing process or the like, a covering layer is formed using a water soluble resin composition on a resist pattern and the covering layer in its part located near the resist pattern is crosslinked to form a modified covering layer which is insoluble in a developing solution on the surface of the resist pattern and covers the resist pattern, thereby effectively reducing the isolation size or hole opening size of the resist pattern to those below the limiting resolution. The present invention also relates to a water soluble resin composition suitable for covering layer formation.

15 Background Art

[0002] In extensive fields including the manufacture of semiconductors such as LSIs, the preparation of flat panel displays (FPDs) such as liquid crystal display (LCD) panels, and the manufacture of circuit boards for thermal heads and the like, photolithography has hitherto been used for the formation of fine elements or microfabrication. In the photolithography, a positive- or negative-working radiation-sensitive resin composition (photoresist) is used for resist pattern formation. The positive- or negative-working photoresist is coated onto a substrate, and mask alignment is conducted, followed by exposure and development to form a resist pattern. The resist pattern thus formed is utilized, for example, as an etching resist and a resist for impurity ion implantation in the manufacture of semiconductor devices, FPDs, and circuit boards, and as a plating resist or the like in the manufacture of magnetic heads or the like.

[0003] In recent years, increased integration density in semiconductor devices or the like has led to an ever-increasing demand for a reduction in wiring or element isolation width required of the manufacturing process. To cope with this demand, various attempts have been made, for example, to increase the fineness of the resist pattern using shorter-wavelength light, to form a finer resist pattern using a phase shift reticle or the like, and to develop a novel resist and a novel process that can meet the demand. In the conventional photolithography utilizing exposure, however, difficulties are encountered in the formation of a resist pattern which is finer than a limit determined by the wavelength of light for exposure. On the other hand, apparatuses for exposure of short wavelength light and apparatuses using a phase shift reticle or the like are disadvantageously expensive. To solve the above problems, a method for pattern formation has been proposed which comprises the steps of:

- (1) providing a conventional positive- or negative-working photoresist and forming a pattern by a conventional method for pattern formation,
- (2) providing an acid-crosslinkable covering layer on the formed resist pattern,
- (3) heating the covered resist pattern to diffuse an acid from the resist pattern to crosslink the covering layer in its part located near the resist pattern to form a modified covering layer insoluble in a developing solution on the surface of the resist pattern, and
- (4) conducting development to remove the covering layer in its part remaining uncured to cover the surface of the resist pattern with the covering layer having a given thickness, whereby the resist pattern width or the opening size in a line-and-space (L/S) pattern is reduced to effectively form a resist pattern which is finer than a resolution limit determined by the wavelength of light for exposure (see, for example, Japanese Patent Laid-Open Nos. 241348/1993, 250379/1994, 73927/1998, and 19860/2001). This method has drawn attention as an effective method, because the size of the space part in the resist pattern can be effectively reduced without large investment of equipment such as an exposure system for short wavelengths.

[0004] The present inventors have made an application (Japanese Patent Application No. 45599/2003) directed to a water soluble resin composition, a method for resist pattern formation using the same, and a method for testing a resist pattern. This water soluble resin composition comprises poly(vinyl pyrrolidone-co-vinyl acetate) or poly(vinyl pyrrolidone-co-vinylimidazole) as a water soluble resin, p-toluenesulfonic acid triethylamine salt as an acid generating agent, and acetylenic alcohol as a surfactant. A covering layer having a satisfactory thickness can be formed with a high dimension accuracy on a highly water repellent resist pattern formed of, for example, a radiation-sensitive resin composition capable of coping with an ArF exposure, whereby the resist pattern can be thickened to effectively reduce the pattern size to such a level that renders the resist pattern finer than the limiting resolution and, at the same time, a change in measured value upon electron beam irradiation in measuring SEM can be prevented.

[0005] The above conventional method in which a resist pattern is covered with a covering layer to reduce the width

between resist patterns in an L/S pattern or reduce the opening size of contact patterns and thus to effectively form a resist pattern which is finer than the limiting resolution determined by wavelength of light for exposure has mainly been intended for a resist pattern formed of a KrF resist (a radiation-sensitive resin composition capable of coping with KrF) and has been effective for the KrF resist. On the other hand, an ArF excimer laser exposure process has recently been proposed for finer resist pattern formation, and this has led to a proposal of an ArF resist (a radiation-sensitive resin composition capable of coping with ArF exposure). Transparency to a 248 nm light source has been required of the conventional KrF resist. On the other hand, the ArF resist should be transparent to a 193 nm light source. This inevitably leads to predominant use of a polymer having a structure comprising a protective group introduced into an acrylic or methacrylic resin or the like. For example, a protective group having an alicyclic structure has been proposed as the protective group. Due to the nature of the structure, the hydrophobicity of the polymer per se is higher than that of the KrF resist. On the other hand, the composition for a covering layer is in many cases a composition composed mainly of a water soluble resin and water from the viewpoint of preventing dissolution of the resist film as the first layer. For this reason, in many cases, the conventional water soluble resin composition for a covering layer has no satisfactory coatability on a highly water repellent resist pattern such as the above ArF resist. This has sometimes made impossible to form a good covering layer or modified covering layer. Further, in some cases, the level of fineness of the resist pattern layer has been unsatisfactory, probably because the diffusion of an acid from the resist pattern is unsatisfactory. Furthermore, in the prior art technique, an increase in complexity of the resist pattern has raised a problem of a difference in size reduction level in a coarse-and-fine pattern of the resist pattern. In Japanese Patent Application No. 45599/2003, it was found that the effective size of a resist pattern formed of a radiation-sensitive resin composition capable of coping with ArF can be reduced to a value beyond the limiting resolution. However, there is a demand for an improvement in pattern size reduction effect, that is, the formation of a thicker modified covering layer.

SUMMARY OF THE INVENTION

[0006] The present invention has been made with a view to solving the above problems of the prior art, and an object of the present invention is to provide a water soluble resin composition that can be applied onto a relatively highly water repellent ArF resist pattern formed by a conventional method to form a covering layer which is then heated for crosslink the covering layer in its part located near the resist pattern to form a modified covering layer insoluble in a developing solution on the surface of the resist pattern and thus to cover the resist pattern with the modified covering layer having a given thickness, that is, to render the resist pattern thick, whereby the isolation size or hole opening size of the resist pattern can be effectively reduced to such a level that renders the resist pattern finer than the limiting resolution with good dimension controllability, and to provide a method for pattern formation using the same.

[0007] According to one aspect of the present invention, there is provided a water soluble resin composition for use in a semiconductor manufacturing process, said semiconductor manufacturing process comprising the steps of: forming a covering layer on a resist pattern formed of a radiation-sensitive resin composition which can cope with ArF exposure; and heating the covered resist pattern to convert the covering layer in its part located near the resist pattern to a modified covering layer and thus to cover the resist pattern with the modified covering layer, whereby the effective size of the resist pattern after etching can be reduced, said water soluble resin composition comprising a water soluble resin, an acid generating agent capable of generating an acid upon heating, a crosslinking agent, and a water-containing solvent.

[0008] According to another aspect of the present invention, there is provided a method for pattern formation, comprising the steps of: coating the above water soluble resin composition onto a resist pattern formed of a radiation-sensitive resin composition capable of coping with ArF exposure to form a covering layer; heating the covering layer to crosslink the covering layer in its part with a predetermined thickness located near the resist pattern to form a modified covering layer insoluble in a developing solution; and developing the modified covering layer to form a pattern in which the surface of the resist pattern has been covered with the modified covering layer.

[0009] In the method for pattern formation according to the present invention, a trench pattern or a hole pattern can be effectively made finer by covering a formed resist pattern with a modified covering layer having a given thickness. When the composition according to the present invention is used, as compared with the conventional composition, the thickness of the modified covering layer can be significantly increased and, at the same time, a change in thickness of the modified covering layer caused by varying the form of the resist pattern, that is, a change in pattern size reduction level, can be reduced. The above effect can realize the production of a semiconductor integrated circuit or the like having an increasing tendency toward increased fineness and complexity at a high yield. Further, the water soluble resin composition according to the present invention advantageously has excellent coatability on the surface of a highly water repellent resist.

BRIEF DESCRIPTION OF THE DRAWINGS


[0010]

Figs. 1A to 1 E are conceptual diagrams illustrating the method for pattern formation according to the present invention.


BEST MODE FOR CARRYING OUT THE INVENTION

[0011] The water soluble resin composition according to the present invention and the method for pattern formation using the water soluble resin will be described in more detail.

[0012] The water soluble resin composition according to the present invention will be first described. The water soluble resin composition according to the present invention comprises at least a water soluble resin, an acid generating agent capable of generating an acid upon heating, a crosslinking agent, and a water-containing solvent. The water soluble resin usable as a raw material of the water soluble resin composition according to the present invention may be any polymer which is publicly known and used in the art so far as the solubility of the polymer in water is not less than 0.1% by weight. Specific examples of water soluble resins include homopolymers of hydrophilic group-containing vinyl monomers and hydrophilic group-containing polycondensates. Examples of such resins include polyvinyl alcohols (including partial saponification products), polyacrylic acids, polymethacrylic acids, poly(2-hydroxy acrylate), poly(2-hydroxyethyl methacrylate), poly(4-hydroxybutyl acrylate), poly(4-hydroxybutyl methacrylate), poly(glycosyloxyethyl methacrylate), polyvinyl methyl ethers, polyvinyl pyrrolidones, polyethylene glycols, polyvinyl acetals (including partial acetalization products), polyethyleneimines, polyethylene oxides, styrene-maleic anhydride copolymers, polyvinylamines, polyallylamines, oxazoline group-containing water soluble resins, water soluble melamine resins, water soluble urea resins, alkyd resins, sulfonamides, or salts of these resins. They may be used either alone or in a combination of two or more. Among these resins, copolymers represented by formula (I) are particularly preferred. The polymer may be either a random polymer or a block polymer. However, the random polymer is particularly preferred.




wherein R^a and R^b each independently represents a hydrogen atom or a methyl group; R^c represents -OH, -COOH, -OCOR^d, where R^d represents an alkyl group, or



and a and b each independently are 10 to 100,000.



[0013] Any molecular weight of the water soluble resin may be selected so far as the effect of the present invention is not sacrificed. From the viewpoint of satisfactory coatability for providing a homogeneous coating film and temporal stability of the coating film, however, the molecular weight is preferably not less than 1000, more preferably not less than 3000. The molecular weight is preferably not more than 1,000,000, more preferably not more than 200,000, from the viewpoints of preventing cobwebbing at the time of coating, keeping good filter permeability, and forming an even coating film using a small dropping amount.

[0014] The acid generating agent according to the present invention is not particularly limited so far as it generates an acid upon heating and is soluble in water. However, an organic acid amine salt which generates an acid upon heating at 70 to 200°C is particularly suitable. In particular, an acid generating agent having a structure of a combination of an acid with a base represented by the following general formula is preferred.



wherein

R^0 represents $-\text{C}_n\text{H}_{2n+1-m}\text{F}_m$ where n is 1 to 20 and m is 0 to $2n + 1$,




where R' is $-(\text{CH}_2)_x\text{CH}_3$, $-\text{OH}$, or $-\text{COOH}$ in which x is 0 to 20; and

R^1 , R^2 , R^3 , and R^4 each independently represent $-\text{H}$, $\text{C}_p\text{H}_{2p+1}$, or $-\text{C}_p\text{H}_{2p}\text{OH}$ where p is 1 to 10.

[0015] Specific examples of acids usable herein include alkylsulfonic acids, fluorinated alkylsulfonic acids, or sulfonic acids having a benzene, naphthalene, or anthracene aromatic skeleton. Specific examples of preferred amines include alkylamines and alkanolamines. More specific examples of acids include p-toluenesulfonic acid, perfluorobutanesulfonic acid, perfluorooctanesulfonic acid, (\pm)camphor-10-sulfonic acid, and dodecylbenzenesulfonic acid. Triethylamine, tripropylamine, and dimethylaminoethanol are suitable as the amine. These acid generating agents may be used either solely or as a mixture of two or more.

[0016] In the present invention, the crosslinking agent is not particularly limited so far as it is soluble in water. Preferred are alkylated urea water soluble crosslinking agents, oxazoline group-containing polymers, and polyamines. The following alkylated urea water soluble crosslinking agents are particularly preferred.





15

20

20

25

30

35

40

45

located near the resist pattern. The covering layer 4 in which the modified covering layer 5 insoluble in the developing solution has been formed is developed to form a pattern in which a modified covering layer 5 is provided on the surface of the resist pattern 3 (Fig. 1 E).

[0024] As described above, the formation of the modified covering layer 5 on the surface (upper surface and side surface) of the resist pattern 3 reduces the width of the resist pattern and can effectively reduce the spacing size or the hole opening size of the resist pattern to those below the limiting resolution.

[0025] The radiation-sensitive resin composition usable in the formation of the resist pattern 3 may be any radiation-sensitive resin composition which is publicly known and used in the art. Radiation-sensitive resin compositions include, for example, positive-working resists containing alkali soluble resins, such as novolak resins, hydroxystyrene resins, or acrylic resins, and quinonediazide compounds, and chemical amplification positive-working or negative-working resists that, upon exposure to light, generate an acid of which the catalytic action is utilized to form a resist pattern. Preferred are chemical amplification positive-working resists that, upon exposure to light, generate an acid of which the catalytic action is utilized to form a resist pattern. In the resist pattern formed from a conventional highly water repellent resist, for example, an ArF resist, difficulties are encountered in the formation of a modified covering layer having satisfactory thickness on a resist pattern by a method in which a water soluble resin covering layer crosslinkable by an acid is formed on a resist pattern and the covering layer is crosslinked through diffusion of the acid from the resist pattern. The composition according to the present invention advantageously has satisfactory coatability on a resist which is relatively highly water repellent as the radiation-sensitive resin composition, for example, an ArF resist. A large number of ArF resists have already been proposed and further are commercially available. Any of these publicly known and used ArF resists may be used. The resist pattern may be formed using the radiation-sensitive resin composition by any conventional method including coating methods, exposure methods, baking methods, development methods, developers, and rinsing methods.

[0026] In the method for pattern formation according to the present invention, the water soluble resin composition according to the present invention for constituting the covering layer may be coated, for example, by any proper method which has hitherto been used in coating the radiation-sensitive resin composition, for example, by spin coating, spray coating, dip coating, or roller coating. The coated covering layer is optionally prebaked to form a covering layer 4. The covering layer is heat treated, for example, under conditions of temperature about 70 to 200°C, heating time period about 60 to 120 sec, preferably about 50 to 80 sec. The temperature at which intermixing between the resist pattern and the covering layer takes place is preferred. The thickness of the covering layer may be properly regulated, for example, by the heat treatment temperature and time and the radiation-sensitive resin composition and water soluble resin composition used. Therefore, these various conditions may be set depending upon the level of the width of resist pattern to be widen. The thickness of the covering layer, however, is generally 0.01 to 100 µm.

[0027] Developers usable for the modified covering layer for leaving the modified covering layer 5 formed by heating while removing the covering layer in its other part include water, mixed solutions composed of water and water soluble organic solvents, and aqueous solutions of alkalis such as TMAH (tetramethyl ammonium hydroxide).

[0028] The following Examples further illustrate the present invention but are not intended to limit it.

Example 1 (Preparation of water soluble resin composition)

[0029] 18.7 g of an aqueous water soluble resin solution (30 wt%) containing polyvinyl pyrrolidone-co-polyvinyl imidazole (molecular weight 75000, copolymer composition vinyl pyrrolidone : vinyl imidazole = 0.76 : 1) as a water soluble resin was dissolved in 79.2 liters of water at room temperature to prepare a solution. 0.65 g of an aqueous p-toluenesulfonic acid triethylamine salt solution (70 wt%) was added to the solution. Subsequently, 1.52 g of 1,3-dimethoxymethyl-4,5-dimethoxyimidazoline (tradename: Nikalac MX-280, manufactured by Sanwa Chemical Co.) as a crosslinking agent and 0.05 g of polyoxyethylene alkyl ether (tradename: Pionion D1420, manufactured by Takemoto Oil & Fat Co., Ltd.) were added thereto, and the mixture was adjusted to have the following weight ratio, followed by thorough stirring for dissolution. The solution was then filtered through a 0.2-µm filter to prepare a water soluble resin composition A.

Table 1

Composition A	Weight ratio
Polyvinyl pyrrolidone-co-polyvinyl imidazole	5.6
p-Toluenesulfonic acid triethylamine salt	0.46
1,3-Dimethoxymethyl-4,5-dimethoxyimidazoline	1.52
Polyoxyethylene alkyl ether	0.05
Water	92.4

Example 2 (Preparation of water soluble resin composition)

[0030] The procedure of Example 1 was repeated, except that the crosslinking agent was changed to urea-formaldehyde-methyl alcohol polycondensate (tradename: Nikalac MX-290, manufactured by Sanwa Chemical Co.) and the mixing ratio of the ingredients was as follows. The mixture thus obtained was thoroughly stirred for dissolution, and the solution was then filtered through a 0.2- μ m filter to prepare a water soluble resin composition B.

Table 2

Composition B	Weight ratio
Polyvinyl pyrrolidone-co-polyvinyl imidazole	7.0
p-Toluenesulfonic acid triethylamine salt	0.52
Urea-formaldehyde-methyl alcohol polycondensate	1.52
Polyoxyethylene alkyl ether	0.05
Water	92.4

Example 3 (Preparation of water soluble resin composition)

[0031] The procedure of Example 1 was repeated, except that the crosslinking agent was changed to N,N'-dimethoxymethyltetrahydro-2-pyrimidone (tradename: Nikalac N1951, manufactured by Sanwa Chemical Co.) and the mixing ratio of the ingredients was as follows. The mixture thus obtained was thoroughly stirred for dissolution, and the solution was then filtered through a 0.2- μ m filter to prepare a water soluble resin composition C.

Table 3

Composition C	Weight ratio
Polyvinyl pyrrolidone-co-polyvinyl imidazole	7.0
p-Toluenesulfonic acid triethylamine salt	0.52
(N,N'-Dimethoxymethyltetrahydro-2-pyrimidone)	1.52
Polyoxyethylene alkyl ether	0.05
Water	92.4

Example 4 (Preparation of water soluble resin composition)

[0032] The procedure of Example 1 was repeated, except that the water soluble resin was changed to polyvinyl pyrrolidone-co-polyvinyl imidazole (molecular weight 75000, copolymer composition vinyl pyrrolidone : vinyl imidazole = 2.24 : 1) and the mixing ratio of the ingredients was as follows. The mixture thus obtained was thoroughly stirred for dissolution, and the solution was then filtered through a 0.2- μ m filter to prepare a water soluble resin composition D.

Table 4

Composition D	Weight ratio
Polyvinyl pyrrolidone-co-polyvinyl imidazole	5.60
p-Toluenesulfonic acid triethylamine salt	0.46
1,3-Dimethoxymethyl-4,5-dimethoxyimidazoline	1.52
Polyoxyethylene alkyl ether	0.05
Water	92.45

Example 5 (Preparation of water soluble resin composition)

[0033] The procedure of Example 1 was repeated, except that the water soluble resin was changed to polyvinyl pyrrolidone-co-polyvinyl imidazole (molecular weight 240000, copolymer composition vinyl pyrrolidone : vinyl imidazole = 0.76 : 1) and the mixing ratio of the ingredients was as follows. The mixture thus obtained was thoroughly stirred for dissolution, and the solution was then filtered through a 0.2- μ m filter to prepare a water soluble resin composition E.

Table 5

Composition E	Weight ratio
Polyvinyl pyrrolidone-co-polyvinyl imidazole	5.6
p-Toluenesulfonic acid triethylamine salt	0.46
1,3-Dimethoxymethyl-4,5-dimethoxyimidazoline	1.52
Polyoxyethylene alkyl ether	0.05
Water	92.4

Comparative Example 1

[0034] For comparison, a water soluble resin composition F for a covering layer (tradename: AZ Exp.R600, manufactured by Clariant (Japan) K.K.) was provided. The water soluble resin composition F had the following composition.

Table 6

Composition F	Weight ratio
Polyvinyl pyrrolidone-co-polyvinyl imidazole* ¹	7.1
p-Toluenesulfonic acid triethylamine salt	0.47
Polyoxyethylene (4) acetylenic glycol ether* ²	0.05
Water	92.4
* ¹ Molecular weight 75000, copolymer composition vinyl pyrrolidone : vinyl imidazole = 1 : 0.76	
* ² Acetylenol EL (tradename), manufactured by Kawaken Fine Chemicals Co., Ltd.	

Formation of contact hole pattern

[0035] An underlying antireflection film AZ ArF-1 C5D (tradename: manufactured by Clariant Corp.) was coated onto an 8 in. silicon wafer by a spin coater (MK-8) manufactured by Tokyo Electron Limited. The coated silicon wafer was prebaked on a hot plate at 200°C for 60 sec. Thereafter, a positive-working photosensitive resin composition AZ AX1050HS (tradename: manufactured by Clariant Corp.) was coated to provide an about 0.022 μm-thick resist film which was then prebaked on a hot plate at 115°C for 60 sec. An exposure system with an exposure wavelength of ArF radiation (193 nm) (NSR-S306C ArF Scanner, manufactured by NIKON CORPORATION) was then provided, and exposure was carried out using a pattern having various contact holes, followed by post exposure baking (PEB) on a hot plate at 110°C for 60 sec. Thereafter, spray paddle development was carried out with an alkaline developing solution (AZ 300 MIF developer (tradename), 2.38 wt% aqueous tetramethyl ammonium hydroxide solution) manufactured by Clariant (Japan) K.K. at 23°C for one min to form a positive-working resist pattern with a hole diameter of 130 nmφ and pitch sizes 260 nm and 780 nm.

Evaluation of hole diameter reduction level

[0036] The water soluble resins A to F were coated on the hole pattern formed above by a spin coater (MK-8) manufactured by Tokyo Electron Limited to provide an about 0.30 μm-thick covering layer, and the patterns were subjected to mixing baking on a hot plate at 160°C for 90 sec. Thereafter, development was carried out with pure water at 23°C for one min to separate the uncured layer. Thus, resist patterns were formed in which a modified covering layer was provided on the contact hole pattern. For the evaluation of hole diameter reduction level, the hole diameter of the hole pattern was measured before and after the modified covering layer formation with a high-precision appearance dimension evaluation apparatus (S-9200) manufactured by Hitachi, Ltd. to determine the change in the measured hole diameter. The results were as shown in Table 7.

Table 7

	Water soluble resin composition	Hole diameter reduction level*		Rate of change in hole diameter reduction level
		Pitch size 260 nm	Pitch size 780 nm	
Ex. 1	A	26.9	31.3	14

(continued)

	Water soluble resin composition		Hole diameter reduction level*		Rate of change in hole diameter reduction level
			Pitch size 260 nm	Pitch size 780 nm	
5	Ex. 2	B	47.3	60.0	21
	Ex. 3	C	32.7	51.3	36
	Ex. 4	D	34.1	43.6	22
	Ex. 5	E	44.3	44.6	0.7
10	Comp. Ex. 1	F	16.6	23.5	29
*: Hole diameter reduction level in the formation of positive-working resist pattern with hole diameter of 130 nmφ.					

Criteria of evaluation

15 **[0037]** The hole diameter reduction level and the rate of change in hole diameter reduction level were determined according to the following equations.

20
$$(\text{Hole diameter reduction level}) (\text{nm}) = (\text{size before insolubilized layer formation}) - (\text{size after insolubilized layer formation})$$


25
$$(\text{Rate of change in hole diameter reduction level}) = \frac{[(\text{hole diameter reduction level in positive-working resist pattern with hole diameter of } 130 \text{ nm}\phi \text{ and pitch size of } 780 \text{ nm}) - (\text{hole diameter reduction level in positive-working resist pattern with hole diameter of } 130 \text{ nm}\phi \text{ and pitch size of } 260 \text{ nm})]}{(\text{hole diameter reduction level in positive-working resist pattern with hole diameter of } 130 \text{ nm}\phi \text{ and pitch size of } 780 \text{ nm})} \times 100$$

35 **[0038]** The results of the measurement of the hole diameter reduction level in Table 7 show that the use of the water soluble resin composition according to the present invention can significantly reduce the hole diameter of the contact hole pattern as compared with the use of the conventional composition (Comparative Example 1). Further, the results of the determination of the rate of change in hole diameter reduction level show that the change in hole diameter reduction level upon a change in a pattern pitch size is comparable to or better than that in the conventional composition. In particular, the results of Example 5 show that the hole diameter becomes significantly small and, at the same time, there is substantially no variation in hole diameter even upon a change in pattern pitch.

45 Claims



1. A water soluble resin composition for use in a semiconductor manufacturing process, said semiconductor manufacturing process comprising the steps of: forming a covering layer on a resist pattern formed of a radiation-sensitive resin composition which can cope with ArF exposure; and heating the covered resist pattern to convert the covering layer in its part located near the resist pattern to a modified covering layer and thus to cover the resist pattern with the modified covering layer, whereby the effective size of the resist pattern after etching can be reduced, said water soluble resin composition comprising a water soluble resin, an acid generating agent capable of generating an acid upon heating, a crosslinking agent, and a water-containing solvent.
2. The water soluble resin composition according to claim 1, wherein said water soluble resin comprises a copolymer of N-vinylpyrrolidone with vinylimidazole.

3. The water soluble resin composition according to claim 1 or 2, wherein said acid generating agent is represented by formula



wherein

R^0 represents $-\text{C}_n\text{H}_{2n+1-m}\text{F}_m$ where n is 1 to 20 and m is 0 to $2n+1$,



where R^1 is $-(\text{CH}_2)_x\text{CH}_3$, $-\text{OH}$, or $-\text{COOH}$ in which x is 0 to 20; and

R^1 , R^2 , R^3 , and R^4 each independently represent $-\text{H}$, $\text{C}_p\text{H}_{2p+1}$, or $-\text{C}_p\text{H}_{2p}\text{OH}$ where p is 1 to 10.

4. The water soluble resin composition according to any one of claims 1 to 3, which further comprises at least one surfactant selected from the group consisting of acetylenic alcohols, acetylenic glycols, polyethoxylates of acetylenic alcohols, and polyethoxylates of acetylenic glycols.
5. The water soluble resin composition according to any one of claims 1 to 4, wherein said water-containing solvent consists of water alone, or a mixture of water with a water soluble organic solvent.
6. The water soluble resin composition according to any one of claims 1 to 5, wherein said crosslinking agent is an alkylated urea, oxazoline group-containing polymer, or polyamines.
7. The water soluble resin composition according to any one of claims 1 to 6, which comprises, based on 100 parts by weight of the water soluble resin composition, 1 to 30 parts by weight of the water soluble resin, 0.01 to 10 parts by weight of the acid generating agent, and 0 to 20 parts by weight of crosslinking agent.
8. A method for pattern formation, comprising the steps of: coating the water soluble resin composition according to any one of claims 1 to 7 onto a resist pattern formed of a radiation-sensitive resin composition capable of coping with ArF exposure to form a covering layer; heating the covering layer to crosslink the covering layer in its part with a predetermined thickness located near the resist pattern to form a modified covering layer insoluble in a developing solution; and developing the modified covering layer to form a pattern in which the surface of the resist pattern has been covered with the modified covering layer.

EP 1 757 989 A1

9. A pattern covered with a modified covering layer, which is composed of resist pattern formed of a radiation-sensitive resin composition capable of coping with ArF exposure and the modified covering layer formed on the surface of the resist pattern, wherein the modified covering layer is formed by coating the water soluble resin composition according to any one of claims 1 to 7 onto the resist pattern to form a covering layer, by heating the covering layer located near the resist pattern to crosslink in its part with a predetermined thickness to form the modified covering layer insoluble in a developing solution and by developing the modified covering layer to form the pattern.

5

10

15

20

25

30

35


40

45

50

55

Fig. 1



INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP2005/006961

A. CLASSIFICATION OF SUBJECT MATTER Int.Cl. ⁷ G03F7/40, H01L21/027		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) Int.Cl. ⁷ G03F7/40, H01L21/027		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Jitsuyo Shinan Koho 1922-1996 Jitsuyo Shinan Toroku Koho 1996-2005 Kokai Jitsuyo Shinan Koho 1971-2005 Toroku Jitsuyo Shinan Koho 1994-2005		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X Y A	JP 2001-228616 A (Mitsubishi Electric Corp., Ryoden Semiconductor System Engineering), 24 August, 2001 (24.08.01), Full text; all drawings & CN 1309416 A & TW 466583 B	1, 5-9 4 2, 3
Y A	JP 2004-46060 A (Fujitsu Ltd.), 12 February, 2004 (12.02.04), Full text; all drawings & EP 1315043 A1 & US 2003/102285 A1 & CN 1421743 A	1, 4-9 2, 3
Y A	JP 2004-77951 A (Fujitsu Ltd.), 11 March, 2004 (11.03.04), Full text; all drawings & EP 1398671 A1 & US 2004/121259 A1 & CN 1477447 A	1, 4-9 2, 3
<input checked="" type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier application or patent but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family		
Date of the actual completion of the international search 21 April, 2005 (21.04.05)		Date of mailing of the international search report 17 May, 2005 (17.05.05)
Name and mailing address of the ISA/ Japanese Patent Office		Authorized officer
Facsimile No.		Telephone No.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP2005/006961

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y A	JP 2001-19860 A (Clariant International Ltd.), 23 January, 2001 (23.01.01), Full text & WO 2001/735 A1 & EP 1152036 A1 & US 6555607 B1 & CN 1314931 A	1, 4-9 2, 3
A	JP 2003-84460 A (Tokyo Ohka Kogyo Co., Ltd.), 19 March, 2003 (19.03.03), Full text & EP 1273974 A2 & US 2003/8968 A1 & CN 1396627 A & TW 544763 B	1-9

Form PCT/ISA/210 (continuation of second sheet) (January 2004)

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 5241348 A [0003]
- JP 6250379 A [0003]
- JP 10073927 A [0003]
- JP 2001019860 A [0003]
- JP 2003045599 A [0004] [0005]